

Duo HT 4 Slates/F C180 Mecano



BBA n° 98/3537



Appraisal No.
685 [2016] NZ



NL-BSD-BD
007



BC2-310-0296-
0123-01



ATG 1924




30060

Description & Application:

A flexible waterproofing membrane with a dual reinforcement and a double polymeric bitumen coating. The upper coating consists of TPO (Thermoplastic PolyOlefins) - modified bitumen, resulting in a high mechanical resistance and is UV resistant. The undercoating consists of SBS (Styrene Butadiene Styrene) - modified bitumen with high elasticity and strong adhesion properties. The composite reinforcement of polyester and glass scrim, (180 g/m²) combine to provide strength and stability. The upper side is finished with optimally pressed in coloured slates and the underside is finished with a sacrificial film. The selvedge with a width of 13 cm is coated with SBS modified bitumen to ensure a SBS-SBS seal. This provides an easy application technique and perfectly sealed joints. With an extra wide selvedge it is especially used as a cap sheet for single layer mechanically fixed applications.

Packaging:

Roll size: 8 m
Roll weight: 37 kg
Number of rolls on a pallet: 23



- * coloured slates
- 1. Upper coating in TPO-plastomer modified bitumen
- 2. Composite reinforcement 180 g/m² of polyester and glass scrim
- 3. Under coating in SBS elastomer bitumen
- ** sacrificial film

Technical Data:

Characteristics	Test Method	Units	Expression of Result	Value
Length x width	EN 1848-1	m x m	MLV ≥	8 x 1
Thickness	EN 1849-1	mm	MDV ± 5%	4
Visual defects	EN 1850-1	-	Pass / No Pass	Pass
Straightness	EN 1848-1	-	Pass / No Pass	Pass
External fire performance	ENV 1187	-	In accordance with EN 13501-5	NPD
Reaction to fire	EN 13501-1	-	In accordance with EN 13501-1	F
Tensile strength (L/T)	EN 12311-1	N/50 mm	MDV ± 20%	880/880
Elongation (L/T)	EN 12311-1	%	MDV ± 15	50
Resistance to static loading	EN 12730	Kg	MLV ≥	L25
Resistance to impact	EN 12691	mm	MLV ≤	I10
Resistance to tearing (nail shank) (LT)	EN 12310-1	N	MDV ± 50	300
Dimensional stability	EN 1107-1	%	MLV ≤	0.3
Flexibility at low temperature TPO/SBS - initial - after aging (EN 1296)	EN 1109	°C °C	MLV ≤	-15/-20 -5/-5



Duo HT 4 Slates/F C180 Mecano

Technical Data continued:

Flow resistance at elevated temperature - initial - after aging (EN 1296)	EN 1110	°C °C	MLV ≥	110 100
Joint strength: peel resistance	EN 12316-1	N/50 mm	MDV ± 50	150
Joint strength: shear resistance	EN 12317-1	N/50 mm	MDV ± 250	750
Water tightness	EN 1928		Pass / No Pass	Pass
Water tightness after stretching at low temperature	EN 13897	%	MLV ≥	10
Adhesion of granules	EN 12039	%	MDV ± 5%	10

MDV: Manufacturer's Declared Value
MLV: Manufacturer's Limiting Value
NPD: No Performances Declared

Health & Safety:

Duo Bitumen Primer is solvent-based and must be used with adequate ventilation. Remove all naked flames and sources of ignition. Adequate ventilation is required to minimise exposure to bitumen fumes during the torching process. Safety Data Sheet (SDS) must be read and understood prior to use of product.

Storage:

Membrane rolls shall be stored in a dry area, always in an upright (vertical) position. Do not lay rolls flat (horizontal) when storing.

Equus Industries Ltd
PO Box 601
Blenheim
Phone: 03 578 0214 Fax 03 578 0919
Email: admin@equus.co.nz
Website: www.equus.co.nz

© Equus Industries Ltd
Edition 6
February 2017